Product Data Sheet Edition 2.5.2018 Sikadur®-72 JNS

## Sikadur<sup>®</sup>-72 JNS

Flexible, abrasion and impactresistant joint nosing mortar

Description	Sikadur-72 JNS is a flexible, abrasion and impact resistant polymer mortar comprised of a two-component, 100% solids, moisture tolerant epoxy resin binder and silica aggregate.	
Where to Use	Use for exterior, above grade concrete surfaces (ie. bridge decks, parking structures and ramps) requiring a flexible, impact and abrasion resistant joint.	
Advantages	<ul> <li>Fast Settling for quick turn around</li> <li>Abrasian and impact resistant</li> <li>Excellent bond to Asphalt and Concrete</li> <li>Flexibility allows for some substrate move</li> </ul>	ement
Coverage	1 can A, 1 can B and 1 bag of part C yield 0.	5 cubic feet of mortar
Packaging	Box cont. 0.5 gal A, 0.5 gal B, 50lb bag of sand	
	Typical Data Material and curing cond	itians @ 72°E (22°C) and 50% B H 1
	<b>Typical Data</b> [Material and curing conditions @ 73°F (23°C) and 50% R.H.] RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.	
	Shelf Life	2 years in original, unopened containers.
	Storage Conditions	Store dry at 40°-95°F (4°-35°C). Condition material to 65°- 85°F (18°-29°C) before using.
	Color	Gray
	Traffic Time	4 hours
	Neat Resin Properties	
	Mixing Ratio	1:1
	Viscosity	Approximately 2000 cps
	Pot Life (ASTM C881)	Approximately 15-20 mins (60g mass)
	Tensile Strength (ASTM D-638)	2650
	Elongation (ASTM D-638)	48%
	Shore D Hardness	72
	Cured Mortar	
	Compressive Strength (ASTM C-579)	<b>1 day</b> 5500 psi
	Bond Strength (ASTM C-882)	<b>2 days</b> 1,300 psi
		<b>14 days</b> 1,800 psi
	* Material cured and tested at the temperatures indicated.	

Construction



PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT HTTP://USA.SIKA.COM/ OR BY CALLING SIKA'S TECHNICAL SERVICE DE-PARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CUR-RENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

How to Use		
Surface Preparation	Surface must be clean and sound. It may be dry or damp, but free of standing water. Remove dust, laitance grease, curing compounds, impregnations, waxes and any other contaminants.	
	<b>Preparation Work: Concrete</b> - Should be cleaned and prepared to achieve a laitance and contaminant free open textured surface CSP 3-4 to CSP-4 by blast cleaning or equivalent mechanical means.	
	Steel - Should be cleaned and prepared thoroughly by blast cleaning to white metal finish.	
Mixing	Parts A and B must be thoroughly mixed together prior to adding part C. Combine parts A and B in a bucket and mix thoroughly for 2 minutes with a low-speed drill and egg-beater mixing blade (i.e. a jiffy mixing paddle), o appropriate mortar mixer. Slowly add part C and continue mixing until aggregate is fully wetted, approximately 3 minutes.	
Application	Place material into joint or repair and tool with a margin trowel to achieve desired for. Press down on material to compact the mortar prior to finishing, in order to ensure the right physical properties are achieved. The height of the mortar must never be greater than that of the substrate, or there is increased risk of damage by snowplows and other forms of impact. Once mortar has been placed in the desired location, it must be compacted in order to achieve proper physical characteristics. This is achieved by pressing down on any exposed mortar surface with a margin trowel or other suitable tool. If done properly, there will be no open pores or voids visible on the surface, and a thin layer of liquid resin will rise to the surface.	
Limitations	<ul> <li>Minimum substrate and ambient temperature 40°F (4°C).</li> <li>Minimum age of concrete before application is 21-28 days depending upon curing and drying conditions.</li> <li>Do not dilute resin. Addition of solvents will prevent proper cure</li> <li>Material is a vapor barrier after cure</li> <li>Not an aesthetic product. Color may alter due to variations in lighting and/or UV exposure.</li> </ul>	

PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT HTTP://USA.SIKA.COM/ OR BY CALLING SIKA'S TECHNICAL SERVICE DE PARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CUR-RENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

KEEP CONTAINER TIGHTLY CLOSED, KEEP OUT OF REACH OF CHILDREN, NOT FOR INTERNAL CONSUMPTION, FOR INDUSTRIAL USE ONLY, FOR PROFESSIONAL USE ONLY.

For further information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety related data. Read the current actual Safety Data Sheet before using the product. In case of emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Safety Data Sheet which are available online at http://usa.sika.com/ or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Safety Data Sheet prior to product use.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDERANYLEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCTINA MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. SALE OF SIKA PRODUCTS ARE SUBJECT SIKA'S TERMS AND CONDITIONS OF SALE AVAILABLE AT HTTP://USA.SIKA.COM/ OR BY CALLING 201-933-8800.

> Fracc. Industrial Balvanera Corregidora, Queretaro

Phone: 52 442 2385800 Fax: 52 442 2250537

C.P. 76920



R

Sika Corporation

201 Polito Avenue Lyndhurst, NJ 07071 Phone: 800-933-7452 Fax: 201-933-6225

Sika Canada Inc. 601 Delmar Avenue Pointe Claire Quebec H9R 4A9 Phone: 514-697-2610 Fax: 514-694-2792

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center. Sika Mexicana S.A. de C.V. Carretera Libre Celaya Km. 8.5



Sika and Sikadur are registered trademarks. Printed in Canada.