

# PRODUCT DATA SHEET

## Sikadur® Hex-300

### HIGH-MODULUS, HIGH-STRENGTH, IMPREGNATING RESIN

#### PRODUCT DESCRIPTION

Sikadur® Hex-300 is a two-component 100% solids, moisture-tolerant, high strength, high modulus epoxies. Sikadur® Hex 300 is compliant with the 2012 and 2009 International Building Codes (IBC) and the 1997 Uniform Building Code (UBC) per ICC-ES Evaluation Report ESR-3288.

#### USES

Sikadur® Hex-300 may only be used by experienced professionals.

- For use as an impregnating resin with the SikaWrap® Structural Strengthening System.
- Sikadur® Hex-300 is used as a seal coat and impregnating resin for horizontal and vertical applications.

#### CHARACTERISTICS / ADVANTAGES

- Long pot life
- Long open time
- Easy to mix
- Tolerant of moisture before, during and after cure
- High strength, high modulus adhesive
- Excellent adhesion to concrete, masonry metals, wood and most structural materials
- Fully compatible and developed specifically for the SikaWrap® System
- High temperature resistance
- High abrasion and shock resistance
- Solvent-free, VOC compliant

#### APPROVALS / STANDARDS

2009 & 2012 International Building Codes (IBC)  
1997 Uniform Building Code (UBC) per ICC-ES Evaluation Report ESR-3288.

#### PRODUCT INFORMATION

Packaging	4 gallon units
Color	Clear, slightly amber
Shelf Life	24 months from date of production if stored properly in original, unopened and undamaged sealed packaging
Storage Conditions	Store dry at 40–95 °F (4–35 °C). Condition material to 65–75 °F (18–24 °C) before using
Viscosity	~500–750 cps.

## TECHNICAL INFORMATION

Compressive Strength		40 °F (4 °C)	73 °F (23 °C)	90 °F (32 °C)	(ASTM D-695)
	3 days	-	8,300 psi (57.2 MPa)	-	
	7 days	1,000 psi (7.1 MPa)	12,000 psi (82.7 MPa)	12,000 psi (82.7 MPa)	
	28 days	-	11,300 psi (77.9 MPa)	-	
	Material cured and tested at the temperatures indicated and 50 % R.H.				
Modulus of Elasticity in Compression	3.8 x 10 <sup>5</sup> psi (2,621 MPa) (7 days)				73 °F (23 °C) 50 % R.H.)
Flexural Strength	11,500 psi (79.3 MPa)				(ASTM D-790) 73 °F (23 °C) 50 % R.H.
	17,800 psi (123 MPa)				140 °F (60 °C) 50 % R.H.
	Post cured min. 48 hrs				
Modulus of Elasticity in Flexure	5.1 x 10 <sup>5</sup> psi (3,517 MPa)				(ASTM D-790) 73 °F (23 °C) 50 % R.H.
	6 x 10 <sup>5</sup> psi (4,138 MPa)				140 °F (60 °C) 50 % R.H.
	Post cured min. 48 hrs				
Tensile Strength	7,500 psi (41.4 MPa)				(ASTM D-638) 73 °F (23 °C) 50 % R.H.
	10,200 psi (70.3 MPa)				140 °F (60 °C) 50 % R.H.
	Post cured min. 48 hrs				
Tensile Modulus of Elasticity	2.8 x 10 <sup>5</sup> psi				73 °F (23 °C) 50 % R.H.
	3.4 x 10 <sup>5</sup> psi (2,345 MPa)				140 °F (60 °C) 50 % R.H.
	Post cured min. 48 hrs				
Elongation at Break	3.2 %				(ASTM D-638) 73 °F (23 °C) 50 % R.H.
	4.8 %				140 °F (60 °C) 50 % R.H.
	Post cured min. 48 hrs				
Heat Deflection Temperature	112 °F (44.5 °C) (7 days) (fiber stress loading = 264 psi (1.8 MPa))				(ASTM D-648)
Water Absorption	0.32 % (7 days (24 hour immersion))				(ASTM D-570)
Service Temperature	-40–140 °F (-40–60 °C)				

## APPLICATION INFORMATION

Mixing Ratio	Mix entire unit, do not batch down
--------------	------------------------------------

<b>Coverage</b>	As a sealer: 100 ft <sup>2</sup> /gal.	
	As an impregnating resin: 120 ft <sup>2</sup> /gal. - 9 oz. per sq.yd. fabrics 60 ft <sup>2</sup> /gal. - 18 oz. per sq.yd. fabrics 30 ft <sup>2</sup> /gal. - 37 oz. per sq.yd. fabrics	
<b>Pot Life</b>	~ 3–4 hours	(1 quart volume mixed)
<b>Open Time</b>	~ 6–7 hours	(Time to reach ~10,000 cps)
<b>Cure Time</b>	~ 12–14 hours	(Tack Free)

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

The concrete surface should be prepared to a minimum concrete surface profile (CSP) 3 as defined by the ICRI-surface-profile chips. Localized out-of-plane variations, including form lines, should not exceed 1/32 in. (1 mm). Substrate must be clean, sound, and free of surface moisture. Remove dust, laitance, grease, oils, curing compounds, waxes, impregnations, foreign particles, coatings and disintegrated materials by mechanical means (i.e. sandblasting). For best results, substrate should be dry. However, a saturated surface dry condition is acceptable.

### MIXING

Pre-mix each component. Mix entire unit, do not batch. Pour contents of part 'B' to part 'A'. Mix thoroughly for 5 minutes using a paddle style mixer on low speed (400–600 rpm) drill until uniformly blended.

### APPLICATION METHOD / TOOLS

**As a sealer:** Apply mixed Sikadur® Hex-300 epoxy to a properly prepared substrate using a brush, roller or airless sprayer. Sikadur® Hex-300 should be applied at a sufficient rate to fully saturate the substrate without producing a surface film. Coverage rates are based on a substrate with normal porosity.

**As an impregnating resin:** For vertical and horizontal applications, use Sikadur® Hex-300. For vertical and overhead applications use Sikadur® 330 US as tack coat/primer for the saturated fabric to prevent it from sliding off. Resins may be applied to fabric by either manual or mechanical means. For further information, consult installation guidelines.

## LIMITATIONS

- Minimum substrate and ambient temperature 40 °F (4 °C)
- Do not thin with solvents
- Material is a vapor barrier after cure
- Minimum age of concrete must be 21–28 days depending on curing and drying conditions
- Not an aesthetic product. Color may alter due to variations in lighting and/or UV exposure

- Mechanically prepared, top side, horizontal concrete surfaces can be primed with Sikadur® Hex-300. Vertical or overhead surfaces however, must be primed with Sikadur® 330 US.

## BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## LOCAL RESTRICTIONS

See Legal Disclaimer.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## LEGAL DISCLAIMER

**KEEP CONTAINER TIGHTLY CLOSED •KEEP OUT OF REACH OF CHILDREN •NOT FOR INTERNAL CONSUMPTION •FOR INDUSTRIAL USE ONLY •FOR PROFESSIONAL USE ONLY**

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA's Technical Service Department at 800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.** Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 201-933-8300.

**Sika Corporation**  
201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: 800-933-7452  
Fax: 201-933-6225

**Sika Canada Inc.**  
601 Delmar Avenue  
Pointe Claire  
Quebec H9R 4A9  
Phone: 514-697-2610  
Fax: 514-694-2792

**Sika Mexicana S.A. de C.V.**  
Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537



Product Data Sheet  
Sikadur® Hex-300  
October 2018, Version 01.01  
020206040020000001

SikadurHex-300-en-US-(10-2018)-1-1.pdf

