

# SITEDRAIN™ STRIP 6400

## PREFABRICATED STRIP DRAIN



### PRODUCT OVERVIEW

SITEDRAIN Strip 6400 geocomposite strip drain products are composed of a dimpled polymeric perforated core fully wrapped in a nonwoven geotextile. The geotextile allows water to pass through while retaining backfill materials. The perforated core allows water collection from all sides and provides a continuous flow path to designated drainage exits.

SITEDRAIN Strip 6400 products provide a value engineered alternative to perforated pipe and aggregate subsurface drainage systems requiring moderate strength, high flow capacity, and a geotextile meeting AASHTO M288 Class 3 subsurface drainage requirements.

PROPERTY <sup>1</sup>	TEST METHOD	UNIT OF MEASURE	Typical Value	MARV
<b>GEOTEXTILE</b>				
Material <sup>2</sup>			PP, NPNW	PP, NPNW
Survivability	AASHTO M288	Class	3	3
Grab Tensile Strength	ASTM D4632	lbs	135	120
		N	601	534
Grab Elongation	ASTM D4632	%	60	50
CBR Puncture	ASTM D6241	lbs	365	340
		N	1,624	1,512
Trapezoidal Tear	ASTM D4533	lbs	60	50
		N	267	222
UV Resistance	ASTM D4355	% / 500 Hrs	70	70
Apparent Opening Size (AOS) <sup>3</sup>	ASTM D4751	sieve	70	70
		mm	0.212	0.212
Permittivity	ASTM D4491	sec <sup>-1</sup>	2.4	1.7
Water Flow Rate	ASTM D4491	gpm / ft <sup>2</sup>	175	140
		Lpm / m <sup>2</sup>	7,130	5,704
<b>CORE</b>				
Compressive Strength	ASTM D6364 ASTM D1621	psf	6,000	-
		kPa	287	-
Thickness	ASTM D5199	in	1.0	-
		mm	25.4	-
In-Plane Flow Rate <sup>4</sup>	ASTM D4716	gpm/ft	21	-
		Lpm/m	261	-

MODEL	WIDTH	ROLL LENGTH	ROLL WEIGHT	ITEM CODE
6406	6"	150'	23 lbs	10400
6412	12"	150'	44 lbs	10410
6412	12"	500'	150 lbs	11340
6418	18"	150'	69 lbs	10420
6418	18"	500'	230 lbs	11350
6424	24"	150'	87 lbs	10430
6424	24"	500'	290 lbs	11170
6436	36"	100'	87 lbs	10440

<sup>1</sup> Unless otherwise noted, all physical and performance properties listed are Typical Value or Minimum Average Roll Value (MARV) as defined in ASTM D4439.

<sup>2</sup> PP = Polypropylene; NPNW = Needle-Punched Nonwoven; WM = Woven Monofilament; SBNW = Spunbonded Nonwoven

<sup>3</sup> Values for AOS represent Maximum Average Roll Value (MaxARV).

<sup>4</sup> In-plane flow rate measured at 3,600 psf (172 kPa) compressive load and a hydraulic gradient of 0.1.

All technical information contained in this document is accurate as of publication. AWD reserves the right to make changes to products and literature without notice. Please refer to our website for the most current technical information available.