



# THIN-TOP SUPREME

## SINGLE COMPONENT CEMENTITIOUS TOPPING & REPAIR MORTAR FOR THIN APPLICATIONS

EUCLID CHEMICAL

### DESCRIPTION

THIN-TOP SUPREME is a latex and microsilica modified cementitious mortar designed for use as a floor or deck topping at thicknesses of 1/16" to 3/8" (1.6 mm to 9.5 mm). This product is a single-component formula which incorporates a powder latex technology. It provides excellent durability under freeze-thaw cycling as well as reducing the ingress of water and de-icing salts. THIN-TOP SUPREME offers normal set times in a trowelable consistency for easy workability.

### PRIMARY APPLICATIONS

- Parking decks
- Pavements
- Joints
- Marine structures
- Curbs and gutters
- Ramps
- Floors
- Walkways

### FEATURES/BENEFITS

- Provides a strong, wear resistant thin overlay
- Excellent durability in freeze-thaw cycles
- Contains an integral corrosion inhibitor
- Excellent bond to prepared concrete
- Reduces the penetration of water and de-icing salts for substrate protection
- Suitable for both interior and exterior use

### TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

**Compressive Strength** ASTM C 109, 2" (50 mm) cubes  
@ 2.9 qts (2.7 L)/50 lb (22.7 kg) bag.

Age	Strength
1 day.....	2,000 psi (13.8 MPa)
7 days.....	4,000 psi (27.6 MPa)
28 days.....	6,000 psi (41.3 MPa)

**Linear Shrinkage** ASTM C 157  
28 days.....-0.15%

**Unit Weight**.....approx. 130 lb/ft<sup>3</sup> (2082 kg/m<sup>3</sup>)

**Flexural Strength** ASTM C 348  
7 days .....1,000 psi (6.9 MPa)  
28 days.....1,200 psi (8.3 MPa)

**Appearance:** THIN-TOP SUPREME is a free-flowing powder as packaged. After mixing and placing, the color may initially appear darker than the surrounding concrete. The color will lighten up substantially as it cures and dries out, though it may always appear somewhat darker than the surrounding concrete.

**Split Tensile Strength** ASTM C 496  
7 days.....300 psi (2.1 MPa)  
28 days.....400 psi (2.8 MPa)

**Freeze/Thaw Resistance** ASTM C 666 Procedure A  
300 cycles ..... 89% relative dynamic modulus

**Working Time** ..... 30 to 40 minutes

**Initial Set** ..... 1 to 1.5 hours

**Final Set** ..... approx. 3 hours

### PACKAGING/YIELD

THIN-TOP SUPREME is packaged in 50 lb (22.7 kg) moisture resistant bags. Yield: 0.43 ft<sup>3</sup>/bag (0.012 m<sup>3</sup>) when mixed with 3 qt (2.8 L) of water. Typical water requirement is 2.75 to 3.5 qt (2.6 to 3.3 L)/bag.

### SHELF LIFE

2 years in original, unopened package

### SPECIFICATIONS/COMPLIANCES

Canadian Food Inspection Agency, MTQ and MTO

HORIZONTAL REPAIR

THIN-TOP SUPREME

MASTER FORMAT #: 03 01 30.61

## DIRECTIONS FOR USE

**Surface Preparation:** Concrete surfaces must be structurally sound, free of loose or deteriorated concrete and free of dust, dirt, paint, efflorescence, oil and all other contaminants. Mechanically abrade the surface to achieve a surface profile equal to CSP 4-6 in accordance with ICRI Guideline 310.2. Properly clean profiled area.

**Priming & Bonding (Horizontal Toppings):** For the best adhesion to concrete, use EUCOFLOOR EPOXY PRIMER seeded with sand as the bonding coat. Refer to the EUCOFLOOR EPOXY PRIMER technical data sheet for full instructions. Alternatively, application of EUCOWELD 2.0 or a scrub coat of THIN-TOP SUPREME to the saturated surface dry (SSD) concrete surface may be used for bonding. The topping material must be placed on the scrub coat before the scrub coat dries out.

**Mixing:** Single bags may be mixed with a drill and “jiffy” mixer. Use a paddle type mortar mixer for large jobs. All material should be in the proper temperature range of 60°F (15°C) to 90°F (32°C). Add the appropriate amount of water 2.75 to 3.5 qt (2.6 to 3.3 L) per bag for the batch size and then add the dry product. Mix for 3 to 5 minutes.

**Placement:** Discharge material from mixer immediately and place on to the repair area. For repairs, spread with a trowel, come-a-long, or square tipped shovel to a thickness that matches the surrounding concrete. Work material into place by floating or troweling. On large areas, use screed strips with a vibratory screeding to level.

**Finishing:** This product is designed for finishing with a float or broom appearance. Do not add additional water to the surface during the finishing operation; use EUCOBAR evaporation retarder. For a hard, flat troweled surface, delay finishing until the product is near final set (approx. 3 hours) to reduce the risk of blistering during troweling.

**Curing and Sealing:** Proper curing procedures are important to ensure the durability and quality of the repair. To prevent surface cracking, cure the material with a high solids curing compound, such as SUPER AQUA-CURE VOX or SUPER DIAMOND CLEAR VOX. Note: **Do not use a solvent based curing compound on this product.** If a curing compound is not desired, cover with polyethylene for a minimum of 3 days. **Do not wet cure.** Always re-establish floor and slab joints when using this product as an overlay.

## CLEAN-UP

Clean tools and equipment with water before the material hardens. Hardened THIN-TOP SUPREME will require removal by mechanical means.

## PRECAUTIONS/LIMITATIONS

- Do not wet cure. Do not use a solvent based curing compound on this product.
- Do not allow repairs to freeze until the material has reached a minimum of 1,000 psi (7 MPa) compressive strength.
- Use only potable water for mixing.
- Do not add admixtures or sand.
- Do not use DURALPREP A.C. as a bonding agent for toppings and overlays done with THIN-TOP SUPREME.
- Do not use material at temperatures below 45°F (7°C) or above 100°F (38°C).
- When necessary, follow the recommendations in ACI 305R “Guide to Hot Weather Concreting” or ACI 306R “Guide to Cold Weather Concreting”.
- No heavy traffic until the product has cured.
- Mixing partial bags may yield variable results; always mix full units.
- Store product in a dry place.
- For repairs and toppings thicker than 3/8” (9.5 mm), use CONCRETE-TOP SUPREME.
- In all cases, consult the Safety Data Sheet before use.

Rev. 01.20

**WARRANTY:** The Euclid Chemical Company (“Euclid”) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid’s installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid’s products for the Buyer’s intended purposes.