



PRODUCT DATA SHEET

LM200 NT

LM200 NT is manufactured using high tenacity polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position.

LM200 NT resists ultra violet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

PROPERTY	TEST METHOD	MARV English	MARV Metric
Grab Tensile	ASTM D-4632	200 MD x 200 CD lbs/ft	900 MD x 900 CD N/m
Grab Tensile Elongation	ASTM D-4632	15%	15%
Trapezoidal Tear	ASTM D-4533	75 MDx75 CD LBS	333 MDx333 CD
CBR Puncture Strength	ASTM D-6241	700 lbs	3120 kpa
Apparent Opening Size (AOS)*	ASTM D-4751	40 US Std. Sieve	0.425 mm
Permittivity	ASTM D-4491	0.05 sec ⁻¹	0.05 sec ⁻¹
Flow Rate	ASTM D-4491	5 Gal/min/sq ft	203 l/min/sq m
UV Resistance (500 hrs)	ASTM D-4355	70%	70%
Roll Dimensions (Width x Length)	12.5'x432'	15'x360'	17.5'x309'
Estimated Roll Weight	200 lbs		

*Minimum Average Roll Valve

Disclaimer: L & M Supply assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. L & M Supply disclaims any and all implied, expressed, or statutory standards, guarantees, or warranties. This includes without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information and product. The property values listed above are subject to change without notice.

Unless otherwise noted, this certification is based on testing conducted by our Quality Assurance & Quality Control testing laboratories at the time of manufacturing. L & M Supply Co., Inc. issued this letter of certification to indicate our commitment to providing our customers with a quality product which will meet or exceed the minimum average roll values in accordance with the applicable American Society for Testing and Materials (ASTM) test method.