



PRODUCT DATA SHEET

SikaQuick[®]-800

Rapid Setting Repair Mortar

PRODUCT DESCRIPTION

SikaQuick[®]-800 is one-part, rapid hardening, early strength gain, cementitious, patching mortar for concrete.

USES

- On grade, above grade and below grade concrete conditions
- Highway overlays and repairs
- Structural repair material for concrete roadways, parking structures, bridges, dams, ramps, runways, warehouse floor & loading docks
- Full depth patching repairs up to 8" deep (> 8" may require multiple lifts)

PRODUCT INFORMATION

Packaging	50 lb (22.7 kg) pail
Appearance / Color	Gray powder
Shelf Life	12 months from date of manufacture if stored properly in original, unopened and undamaged, sealed packaging
Storage Conditions	Store dry at 40° - 95° F (4° - 35° C) Protect from moisture. If damp, discard material.

CHARACTERISTICS / ADVANTAGES

- Rapid hardening as defined by ASTM C 928
- Epoxy coatings can be applied as early as 6 hours at 73° F (23° C)
- Freeze / thaw resistant
- Easy to mix and apply - labor-saving
- Not gypsum-based
- High early strength
- Fast setting
- Open to foot traffic in 2 hours / Open to vehicular traffic in 3 hours at 73°F (23° C)

APPROVALS / STANDARDS

- Meets ASTM C 928, Type R3

TECHNICAL INFORMATION

Compressive Strength	Age	73° F (23° C)	(ASTM C 109) 50 % R.H.
	3 hrs.	3,500 psi (24.1 MPa)	
	1 day	6,000 psi (41.4 MPa)	
	7 day	7,000 psi (48.3 MPa)	
	28 day	8,500 psi (58.6 MPa)	

Splitting Tensile Strength	28 days	500 psi (3.4 MPa)	(ASTM C 496) 73° F (23° C) 50% R.H.
-----------------------------------	---------	-------------------	---

Shrinkage	28 day	≤ 0.06% Air Cure ≤ 0.03% Water Cure	(ASTM C 157 mod. per ASTM C 928) 73° F (23° C) 50% R.H.
------------------	--------	--	--

APPLICATION INFORMATION

Mixing Ratio	6 - 6.5 pints (2.8 - 3.1 L)
---------------------	-----------------------------

Coverage	0.43 ft ³ (0.012 m ³) (Yield figures do not include allowance for surface profile, porosity or material waste)
-----------------	--

Layer Thickness	Minimum*	Maximum (per lift)
	Neat	1/2" 8"*

- Do not feather edge

* Minimum thickness is 1/2" (12.7 mm) with the use of SikaQuick® Winter Boost

Product Temperature	65° - 75° F (7° C)
----------------------------	--------------------

Ambient Air Temperature	> 45° F (7° C) 20° - 45° F (-7° - 7° C) with the use of SikaQuick® Winter Boost
--------------------------------	--

Substrate Temperature	> 45° F (7° C) 20° - 45° F (-7° - 7° C) on a frost-free surface with the use of SikaQuick® Winter Boost
------------------------------	--

Set Time	20 -40 minutes	(ASTM C 266) 73° F (23° C) 50% R.H.
-----------------	----------------	---

Final Set Time	35 - 50 minutes	(ASTM C 266) 73° F (23° C) 50% R.H.
-----------------------	-----------------	---

Application Time	Approximately 15 minutes Product temperature will affect the Application Time: <ul style="list-style-type: none">▪ Above 73° F (23° C) will reduce the Application Time and workability▪ Below 73° F (23° C) will extend the Application Time and workability
-------------------------	---

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

- Concrete surface must be clean and sound.
- Remove all deteriorated concrete, dirt, oil, grease, and other bond-inhibiting materials from the area to be repaired.
- Be sure repair area is not less than 1/2" in depth.
- Preparation work should be done by high pressure water blast, scabbling or other appropriate mechanical means to obtain an exposed aggregate surface profile of $\pm 1/8"$ (3 mm) [minimum CSP-6].
- To ensure optimum repair results, the effectiveness of decontamination and preparation should be assessed by a Tensile Adhesion Strength (pull-off) test.
- Saw cutting perimeter edges of concrete repair area at a dovetail angle is preferred.
- Substrate should be Saturated Surface Dry (SSD) with clean water prior to application. No standing water should remain during application.
- Rust, scale, mortar, concrete, dust and other loose and deleterious material which reduces bond or contributes to corrosion shall be removed from steel reinforcement.

MIXING

- Wet down all tools and mixer to be used.
- Pour 6 pints (2.8 L) of clean potable water [approximately 70° F (23° C)] into a suitably sized and clean mixing container, using a calibrated measuring jug or similar, to ensure strict control of the water content.
- Add 1 pail while continuing to mix with a low-speed drill (400-600 rpm) and mortar mixing paddle or in an appropriate mortar mixer.
- Once all the powder has been added, mix to a uniform consistency, maximum 3 minutes, until a lump-free blend is achieved.
- Add up to an additional 1/2 pint (0.24 L) maximum of liquid to achieve desired consistency. Do not over-water.
- Thorough mixing and proper proportioning of the powder and liquid is necessary.
- Inaccurate proportioning of the powder to liquid will result in a finished product that may not conform to the typical published performance property values.

APPLICATION

- A neat mix of SikaQuick®-800 mortar must be scrubbed into the mechanically prepared, SSD substrate. Be sure to work into all pores and voids.
- Force material against edge of repair, working toward center. After filling repair area, screed off excess.
- Allow material to set to desired stiffness, then finish with wood or sponge float for a smooth finish, or broom or burlap-drag for a rough finish.
- If a smoother finish is desired, a magnesium float should be used.
- Mixing, placing, and finishing should not exceed 15

minutes maximum.

- Refer to ACI 305 the "Guide to Hot Weather Concreting" or ACI 306 the "Guide to Cold Weather Concreting" when there is a need to place this product while either hot or cold temperatures prevail. Thinner placements will be more sensitive to the temperature conditions.

CURING TREATMENT

- As per ACI recommendations for Portland cement concrete, curing is required.
- Moist cure with wet burlap and polyethylene, a fine mist of water or Sika® Antisol®-250W*.
- Curing compounds adversely affect the adhesion of following lifts of mortar, leveling mortar or protective coatings.
- Moist curing should commence immediately after finishing. Protect freshly applied mortar from direct sunlight, wind, rain, and frost.

*pretest of curing compound is recommended

LIMITATIONS

- For larger and thicker pours, please contact Sika's Technical Service.
- Addition of 3/8" aggregate can be considered to optimize the yield.
- Avoid application in direct sunlight, during precipitation and/or when strong winds prevail.
- Use only clean, potable water.
- As with all cement-based materials, avoid contact with aluminum to prevent adverse chemical reaction and possible product failure.
- Insulate potential areas of contact by coating aluminum bars, rails, posts etc. with an appropriate epoxy such as Sikadur®-32 Hi-Mod.
- Bonding agents (e.g. Sika® Armatec® 110 EpoCem) should not be used. Use of the neat mortar as a scrub coat is recommended and preferred. If bonding agents are used, follow cure times for the bonding agents used as a guide prior to putting SikaQuick®-800 in service. Assure suitability with the manufacturer of the bonding agent. SikaQuick®-800 does not form a vapor barrier when cured.
- Refer to Sika® Antisol®-250 W product data sheet for use.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet

SikaQuick®-800
March 2020, Version 01.04
020302040040000026

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

SikaQuick-800-en-US-(03-2020)-1-4.pdf

