

Product Description

EXOAIR® Termination Mastic is a single component mastic formulated from polymers, plasticizers and select additives. It is carefully blended to ensure elasticity, weather resistance and durability with ease of application.

Basic Uses

EXOAIR Termination Mastic is designed to seal T-joints, overlaps in detail areas, and as a repair mastic for EXOAIR 110, EXOAIR TWF, EXOAIR 120 and EXOAIR 220.

Availability

EXOAIR Termination Mastic is immediately available from your local Tremco Sales Representative or Distributor. For Distributor locations, visit www.tremcosealants.com

Packaging

28.7 oz (850 mL) Quart Cartridges

Colors

Black

Storage

Store EXOAIR Termination Mastic in original, undamaged packaging in a clean, dry, protected location with temperatures between 40 to 110 °F (5 to 43 °C).

Limitations

- Do not used in a fully encapsulated area

Warranty

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Products proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL VALUES
Maximum V.O.C.	ASTM D3960	300 g/L
Asbestos content	EPA/600/R-93/116	None
Viscosity @ 25 °C (77 °F)	ASTM D2196	600-2,000 Pa·s (600,000-2,000,000 cP)
Density @ 25 °C (77 °F)	ASTM D1475	8.1 lb/gal (970 kg/m³)
Nonvolatile matter	ASTM D4586	70%
Tensile Strength @ 25 °C (77 °F)	ASTM D412	207-690 kPa (30 - 100 psi) @ 100% elongation
Elongation @ 25 °C (77 °F)	ASTM D412	1,000%
Elongation @ -34 °C (-30 °F)	ASTM D412	100%
Recovery from 500% elongation	ASTM D412	90% min
Moisture vapor transmission rate	ASTM F1249	0.42 g/100 in²/24 hrs
Behavior @ 60 °C (140 °F) (Sag Resistance)	ASTM D4586	6 mm (max) (1/4" max)
Flexibility @ -40 °C (40 °F)	ASTM D311	No Cracking



0917/EXOTERM-AB

Tremco Commercial Sealants & Waterproofing

3735 Green Rd
Beachwood OH 44122
216.292.5000 / 800.321.7906

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1445 Rue de Coulomb
Boucherville QC J4B 7L8
514.521.9555