

Product Description

TREMproof® 201/60 is a high-solids, VOC compliant, modified polyurethane waterproofing membrane. It is a one-part moisture-curing elastomer available in three viscosities: Self-Leveling (SL), Roller (R) and Trowel. (Trowel grade intended for detailing work only).

Basic Uses

TREMproof 201/60 is designed for use on backfilled walls, split slabs that slopes to drain, primarily on concrete, masonry and plywood.

Features and Benefits

- TREMproof 201/60 is an economical choice for when construction schedules are not compressed.

Availability

Immediately available from your local Tremco Sales Representative or Distributor. For Distributor locations, visit www.tremcosealants.com.

Coverage Rates

Approximately 25 ft²/gal (0.61 M²/L) at 60 wet mils

Packaging

5-gal (19-L) pails, 36 pails/pallet

55-gal (208-L) drums, 4 drums/pallet

Limitations

- Not for use in submerged or gas vapor conditions.
- Do not apply to damp or contaminated surfaces.
- Not to be used as an exposed or wearing surface.
- Not approved for direct contact with asphalt-based products.
- Use with adequate ventilation.
- Contact your local Tremco Sales Representative or Tremco Technical Services for compatibility information and job-specific recommendations on tie-in and termination details.

Warranty

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Products proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	DESCRIPTION	
Type	Modified Polyurethane Waterproofing	
Color	Black	
Solids	No less than 85%*	
Application	Roller/Trowel/Squeegee	
Thickness	60 mils	
PROPERTY	TEST METHOD	TYPICAL VALUES
Adhesion-in-Peel after Water Immersion (Unprimed)	ASTM C836; ASTM C 794	8 lbf/in (14.00 N/cm)
Weight Loss 20% maximum Loss 80% Solids minimum	ASTM C836; ASTM C 1250	9 to 12% Loss 88 to 92% Solids
Low Temperature Crack Bridging	ASTM C836; ASTM C1305	Pass
Extension after heat aging No observable cracking	ASTM C836; ASTM C1522	Pass
Hardness, Type 00 50 Min.	ASTM C836; ASTM D 2240	58 to 64
Maximum V.O.C.	Method 310	No more than 95 g/L*
Shelf Life Stability	6 months	12 months
Application Temperature	Above 40 °F (5 °C) and rising. If installing below 40 °F (5 °C), please contact Tremco Technical Service at 866-209-2404.	
Storage Temperature	40 to 100 °F (5 to 37 °C)	

*Varies Depending on grade of material used.

**Modified ASTM C1305

0916/TP201-60DS-BG

Tremco Commercial Sealants & Waterproofing

3735 Green Rd
Beachwood OH 44122
216.292.5000 / 800.321.7906

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1445 Rue de Coulomb
Boucherville QC J4B 7L8
514.521.9555

