

Product Description

TREMproof® 250GC is a rapid-curing, high-solids, VOC-compliant modified polyurethane waterproofing membrane that can be applied to damp and green concrete. TREMproof 250GC is a one-part moisture-curing elastomer available in three viscosities: Self-Leveling (SL), Roller (R) and Trowel (trowel intended for detailing work only).

Basic Uses

TREMproof 250GC is designed for use on backfilled walls, split slab applications, planters and submerged conditions. TREMproof 250GC is a complementary waterproofing membrane that can be used with Tremco's Vegetated Roofing systems. Concrete masonry units and plywood are both acceptable substrates.

Features and Benefits

- TREMproof 250GC can be applied in as little as 24 hours following the removal of concrete forms. It can also be applied to damp concrete, reducing the delays associated with rain or other sources of moisture.
- The unique ability to catalyze TREMproof 250GC-SL with water when desired will speed cure times, especially in cold temperatures and low relative humidity, to further condense the construction schedule.
- TREMproof 250GC can be applied at a rate of up to 120 mils in a single lift to speed application without sacrificing performance.
- It can also be applied in multiple lifts to achieve a 215-mil high-build system when maximum protection is required.

Availability

Immediately available from your local Tremco Sales Representative or Distributor. For Distributor locations, visit www.tremcosealants.com.

Coverage Rates

Approximately 25 ft²/gal (0.61 M²/L) at 60 wet mils

Approximately 18 ft²/gal (0.44 M²/L) at 90 wet mils

Approximately 13 ft²/gal (0.32 M²/L) at 120 wet mils

Approximately 7.5 ft²/gal (0.19 M²/L) at 215 wet mils

Packaging

5-gallon (19-L) pails, 36 pails/pallet

55-gallon (208-L) drums, 4 drums/pallet

Applicable Standards

TREMproof 250GC meets or exceeds the following specifications:

- ASTM C836 Standard Specifications for High Solids Content, Cold Liquid-Applied Elastomeric Waterproofing Membrane for Use with Separate Wearing Course
- City of Los Angeles (COLA) approval standards
- Miami-Dade County Acceptance

Limitations

- Do not apply to contaminated surfaces.
- Not to be used as an exposed or wearing surface.
- Use with adequate ventilation.
- Concrete forms must be removed a minimum of 24 hours before TREMproof 250GC can be applied.
- Not approved for direct contact with asphalt-based products.
- Not for use with potable water.
- Contact your local Tremco Sales Representative or Tremco Technical Service for compatibility information and job-specific recommendations on tie-in and termination details.
- Do not apply over a curing or forming oil compound.
- Do not apply over a non-vented metal pan decking substrate without contacting your local Tremco Sales Representative.
- Backfilled applications require the use of a compatible Tremco protection course.
- Applied product should not be left uncovered to UV exposure longer than 120 days or covered with a protection course longer than 120 days.
- Where asphaltic membranes, self-adhering flashing or self-adhering sheet membranes, come in contact with TREMproof 250GC, Tremco Epoxy Primer is to be used at the overlap condition.

Warranty

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Products proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TYPICAL PHYSICAL PROPERTIES

| PROPERTY | DESCRIPTION | |
|--|--|--|
| Composition | Modified Polyurethane Waterproofing | |
| Color | Black | |
| Solids | No less than 84%* | |
| Grade(s) | Trowel, Roller and Self-Leveling | |
| Cure Time | 6 to 12 hr at 75 °F (24 °C), 50% RH | |
| Thickness | 60 mils | |
| PROPERTY | TEST METHOD | TYPICAL VALUES |
| Film Thickness | ASTM C836 | 60 wet mils |
| Tensile Strength | ASTM D412 | 200 psi |
| Elongation | ASTM D412 | 600% |
| Adhesion-in-Peel after Water Immersion (Unprimed) | ASTM C836; ASTM C 794 | 17 lbf/in (29.77 N/cm) |
| Low-Temp Flexibility | ASTM C836; ASTM C 836 | Pass |
| Weight Loss 20% maximum Loss 80% Solids minimum | ASTM C836; ASTM C 1250 | 15% Loss maximum 85% Solids minimum |
| Low Temperature Crack Bridging | ASTM C836; ASTM C1305 | Pass |
| Extension after heat aging No observable cracking | ASTM C836; ASTM C1522 | Pass |
| Hardness, Type 00 50 Min. | ASTM C836; ASTM D 2240 | 87 |
| Water Vapor Permeability | ASTM C836; ASTM E96 Dry Cup ASTM C836; ASTM E96 Wet Cup ASTM C836; ASTM E96 Inverted Wet Cup | 0.02 US Perm-Inch 0.03 US Perm-Inch 0.03 US Perm-Inch |
| Maximum V.O.C. | Method 310 | No more than 177 g/L* (LV formulation does not exceed 100 g/L) |
| Shelf Life Stability 6 Months Minimum | 6 months | 12 months |
| Application Temperature | Above 40 °F (5 °C) and rising. If installing below 40 °F (5 °C), please contact Tremco Technical Services at 866-209-2404. | |
| Storage Temperature | 40 to 100 °F (5 to 37 °C) | |

*Varies Depending on grade of material used.

**Modified ASTM C1305



1219TP250GCDS-BG

Tremco Commercial Sealants & Waterproofing

3735 Green Rd
Beachwood OH 44122
216.292.5000 / 800.321.7906

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1445 Rue de Coulomb
Boucherville QC J4B 7L8
514.521.9555